







			<b>Artline Wood</b>
<b>DESCRIPTION</b>			
Total thickness	EN 428	mm	2
Thickness of wearlayer	EN 429	mm	0.3
Weight	EN 430	g/m <sup>2</sup>	3715
Tile size	EN 427	mm	
Plank size	EN 427	mm	101.6 x 914.4
<b>CLASSIFICATION</b>			
Norm / Product specification			EN 649
European classification	EN 685	class	22
K rating	-	class	
Fire rating	EN 13 501-1	class	B <sub>fl</sub> -s1
Static electrical propensity	EN 1815	kV	<2
Slip resistance wet: ramp test with oil	DIN 51130	class	
<b>PERFORMANCE</b>			
Wear resistance	EN 660.1	mm	≤0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤0.15
Residual indentation	EN 433	mm	≤0.1
Impact sound insulation	EN ISO 717-2	dB	
Thermal conductivity	EN 12524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥6
Chemical products resistance	EN 423	-	OK
Surface treatment	-	-	PUR
<b>MARQUAGE CE</b>			
	EN 14041		   

			<b>Artline Wood</b>
<b>DESCRIPTION</b>			
Total thickness	EN 428	mm	2,5
Thickness of wearlayer	EN 429	mm	0,3
Weight	EN 430	g/m <sup>2</sup>	4695
Tile size	EN 427	mm	
Plank size	EN 427	mm	152 x 914
<b>CLASSIFICATION</b>			
Norm / Product specification			EN 649
European classification	EN 685	class	22
K rating	-	class	
Fire rating	EN 13 501-1	class	B <sub>fl</sub> -s1
Static electrical propensity	EN 1815	kV	<2
Slip resistance wet: ramp test with oil	DIN 51130	class	
<b>PERFORMANCE</b>			
Wear resistance	EN 660.1	mm	≤0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤0.15
Residual indentation	EN 433	mm	≤0.1
Impact sound insulation	EN ISO 717-2	dB	
Thermal conductivity	EN 12524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥6
Chemical products resistance	EN 423	-	OK
Surface treatment	-	-	PUR
<b>MARQUAGE CE</b>			
	EN 14041		