












			CLASSIC IMPERIAL 2mm
DESCRIPTION			
Total thickness	EN 428	mm	2
Weight	EN 430	g/m ²	3460
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
Tile size	EN 427	mm	
Number of tiles per package	-	-	
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	K5
Fire rating	EN 13 501-1	class	B _{fl} s1
Critical radiant flux	ASTM E648	W/cm ²	
Marine Equipment Directive	Directive 96/98/EC		
International Maritime Organisation	I.M.O code F.T.P.	n°	WARRINGTON 164.112/1121/WCL MED0177TE
Static electrical propensity	EN 1815	kV	< 2
Electrical resistance	EN 1081	Ohm	≥ 1 x 10 ⁹
Slip resistance wet: ramp test with oil	DIN 51130	class	R9
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.20
Wear Group	EN 649	group	M
Dimensional stability	EN 434	%	≤ 0.4
Residual indentation	EN 433	mm	~ 0.03
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	class	OK
Anti-bacterial and fungicidal treatment	-	-	OK
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		   

CLASSIC IMPERIAL 2mm			
DESCRIPTION			
Total thickness	EN 428	mm	2
Weight	EN 430	g/m ²	3460
Width of sheet	EN 426	cm	
Length of sheet	EN 426	lm	
Tile size	EN 427	mm	300 x 300
Number of tiles per package	-	-	50
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	K5
Fire rating	EN 13 501-1	class	B _{fl} s1
Critical radiant flux	ASTM E648	W/cm ²	
Marine Equipment Directive	Directive 96/98/EC		
International Maritime Organisation	I.M.O code F.T.P.	n°	WARRINGTON 164.112/1121/WCL MED0177TE
Static electrical propensity	EN 1815	kV	2
Electrical resistance	EN 1081	Ohm	≥ 1 x 10 ⁹
Slip resistance wet: ramp test with oil	DIN 51130	class	R9
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.20
Wear Group	EN 649	group	M
Dimensional stability	EN 434	%	≤ 0.25
Residual indentation	EN 433	mm	~ 0.03
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	class	OK
Anti-bacterial and fungicidal treatment	-	-	OK
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		   

			CLASSIC IMPERIAL 2mm
DESCRIPTION			
Total thickness	EN 428	mm	2
Weight	EN 430	g/m ²	3460
Width of sheet	EN 426	cm	
Length of sheet	EN 426	lm	
Tile size	EN 427	mm	608 x 608
Number of tiles per package	-	-	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
K rating	-	class	K5
Fire rating	EN 13 501-1	class	B _{fl} s1
Critical radiant flux	ASTM E648	W/cm ²	
Marine Equipment Directive	Directive 96/98/EC		
International Maritime Organisation	I.M.O code F.T.P.	n°	WARRINGTON 164.112/1121/WCL MED0177TE
Static electrical propensity	EN 1815	kV	< 2
Electrical resistance	EN 1081	Ohm	≥ 1 x 10 ⁹
Slip resistance wet: ramp test with oil	DIN 51130	class	R9
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.20
Wear Group	EN 649	group	M
Dimensional stability	EN 434	%	≤ 0.25
Residual indentation	EN 433	mm	~ 0.03
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	class	OK
Anti-bacterial and fungicidal treatment	-	-	OK
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		