








			NERA CONTRACT PIXEL
DESCRIPTION			
Total thickness	EN 428	mm	2,25
Thickness of wearlayer	EN 429	mm	0.70
Weight	EN 430	g/m ²	2815
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.05
Impact sound insulation	EN ISO 717-2	dB	5
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		   

			NERA CONTRACT PIXEL
DESCRIPTION			
Total thickness	EN 428	mm	2,25
Thickness of wearlayer	EN 429	mm	0.70
Weight	EN 430	g/m ²	2815
Width of sheet	EN 426	cm	400
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.05
Impact sound insulation	EN ISO 717-2	dB	5
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		   

			NERA CONTRACT WOOD
DESCRIPTION			
Total thickness	EN 428	mm	2,25
Thickness of wearlayer	EN 429	mm	0.70
Weight	EN 430	g/m ²	2815
Width of sheet	EN 426	cm	200
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.05
Impact sound insulation	EN ISO 717-2	dB	5
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		   

NERA CONTRACT WOOD			
DESCRIPTION			
Total thickness	EN 428	mm	2,25
Thickness of wearlayer	EN 429	mm	0.70
Weight	EN 430	g/m ²	2815
Width of sheet	EN 426	cm	400
Length of sheet	EN 426	lm	20
CLASSIFICATION			
Norm / Product specification			EN 649
European classification	EN 685	class	34 - 43
Fire rating	EN 13 501-1	class	B _{fl} s1
Static electrical propensity	EN 1815	kV	< 2
PERFORMANCE			
Wear resistance	EN 660.1	mm	≤ 0.08
Wear group	EN 649	-	T
Dimensional stability	EN 434	%	≤ 0.40
Residual indentation	EN 433	mm	≤ 0.05
Impact sound insulation	EN ISO 717-2	dB	5
Thermal conductivity	EN 12 524	W/(m.K)	0,25
Colour fastness	EN 20 105 - B02	degree	≥ 6
Chemical products resistance	EN 423	-	OK
Anti-bacterial and fungicidal treatment	-	-	Sanosol®
Surface treatment	-	-	PUR
MARQUAGE CE			
	EN 14041		  